



与色同行
及彩共赢

WALKING WITH
COLOR
WIN-WIN WITH
COLOR



Sunnypow Chemicals

销售热线Hotline

邮箱Email

+86 15274877979

info@sunnypow.com

总部地址Headquarters Address

湖南长沙雨花区绿地城际空间站T5栋32层
32nd floor, Building T5, Greenland Intercity Space Station,
Yuhua District, Changsha, Hunan

安徽铜陵生产基地Anhui Tongling Production Base

安徽省铜陵市铜官大道化工产业园
Tongguan Avenue Chemical Industry Park, Tongling City,
Anhui Province

甘肃生产基地Gansu production base

金塔工业集中区北河湾循环经济产业园
Beihewan Circular Economy Industrial Park, Jintan Industrial
Concentration Zone

内蒙古生产基地Inner Mongolia production base

内蒙古鄂尔多斯托克经济开发区
Ordos Economic Development Zone, Inner Mongolia

氧化铁颜料
专业制造商

Iron Oxide Pigment
Specialist Manufacturer




Sunnypow















Sunnypow Chemicals

FACTORY SCENERY 工厂实景



















APPLICATION 产品应用



产品 Product	原色 Masstone	钛白粉冲淡色 TiO ₂ reduction 1:4	备注 Remark	Fe ₂ O ₃	吸油量 Oil abs.	筛余物 325 mesh residue	水溶物 Water sol.matter	水份 Moisture	pH值 pH value
				最小 min. %	g/100g approx.	最大 max. %	最大 max. %	最大 max. %	
氧化铁红	 Iron Oxide Red F110			96	15~25	0.3	0.3	1.0	3~7
	 Iron Oxide Red Y101			96	15~25	0.3	0.3	1.0	3~7
	 Iron Oxide Red F120			96	15~25	0.3	0.3	1.0	3~7
	 Iron Oxide Red 130S			96	15~25	0.3	0.3	1.0	3~7
	 Iron Oxide Red 130A			96	15~25	0.3	0.3	1.0	3~7
	 Iron Oxide Red 140			96	15~25	0.3	0.3	1.0	3~7
	 Iron Oxide Red 190			96	15~25	0.3	0.3	1.0	3~7
	 Iron Oxide Red 180			96	15~25	0.3	0.3	1.0	3~7

产品 Product	原色 Masstone	钛白粉冲淡色 TiO ₂ reduction 1:4	备注 Remark	Fe ₂ O ₃	吸油量 Oil abs.	筛余物 325 mesh residue	水溶物 Water sol.matter	水份 Moisture	pH值 pH value
				最小 min. %	g/100g approx.	最大 max. %	最大 max. %	最大 max. %	
氧化铁黄	 Iron Oxide Yellow 311			86	25~35	0.3	0.3	1.0	3~7
	 Iron Oxide Yellow 313			86	25~35	0.3	0.3	1.0	3~7
	 Iron Oxide Yellow 810			86	25~35	0.3	0.3	1.0	3~7
	 Iron Oxide Yellow 918			86	25~35	0.3	0.3	1.0	3~7
	 Iron Oxide Yellow 8311D			86	21~26	0.1	0.5	1.0	3~7
	 Iron Oxide Yellow 8313D			86	21~26	0.1	0.5	1.0	3~7
	 Heat Stable Yellow 810T			75	35~45	0.3	1.0	1.5	5~8
	 Heat Stable Yellow 980T			65	25~35	0.3	0.5	0.5	5~8

产品 Product	原色 Masstone	钛白粉冲淡色 TiO ₂ reduction 1:4	备注 Remark	Fe ₂ O ₃	吸油量 Oil abs.	筛余物 325 mesh residue	水溶物 Water sol.matter	水份 Moisture	pH值 pH value
				最小 min. %	g/100g approx.	最大 max. %	最大 max. %	最大 max. %	
氧化铁黑	 Iron Oxide Black 318			95	15~25	0.5	0.5	1.5	5~8
	 Iron Oxide Black 330			95	15~25	0.5	0.5	1.5	5~8
	 Iron Oxide Black 750			95	15~25	0.5	0.5	1.5	5~8
	 Iron Oxide Black 760			95	15~25	0.5	0.5	1.5	5~8
	 Iron Oxide Black 8320			95	15~25	0.5	0.5	1.5	5~8
	 Iron Oxide Black 8370			95	15~25	0.5	0.5	1.5	5~8
	 Iron Oxide Black 8390			95	15~25	0.5	0.5	1.5	5~8
	 Heat Stable Black 750T			65	20~30	0.3	1.5	0.5	5~8

产品 Product	原色 Masstone	钛白粉冲淡色 TiO ₂ reduction 1:4	备注 Remark	Fe ₂ O ₃	吸油量 Oil abs.	筛余物 325 mesh residue	水溶物 Water sol.matter	水份 Moisture	pH值 pH value
				最小 min. %	g/100g approx.	最大 max. %	最大 max. %	最大 max. %	
氧化铁橙	 Iron Oxide Orange 960			88	20~30	0.3	0.3	1.0	3.5~7
	 Iron Oxide Brown 610			88	20~30	0.3	0.5	1.5	3.5~7
氧化铁棕	 Iron Oxide Brown 686			88	20~30	0.3	0.5	1.5	3.5~7
	 Compound Ferric Green 835			----	25~35	0.3	3.0	1.0	6~9
复合铁蓝	 Compound Ferric Blue BL-026			----	25~35	0.3	3.0	1.0	6~9
产品 Product	原色 Masstone	钛白粉冲淡色 TiO ₂ reduction 1:4	备注 Remark	砷 As (ppm)	铅 Pb (ppm)	铬 Cr (ppm)	镉 Cd (ppm)	汞 Hg (ppm)	镍 Ni (ppm)
				最大 max. %	最大 max. %	最大 max. %	最大 max. %	最大 max. %	最大 max. %
烟草级氧化铁	 Tobacco Grade Iron Oxide Yellow Y-588			3.0	10.0	100	1.0	1.0	200
	 Tobacco Grade Iron Oxide Red DS110			5.0	15.0	100	3.0	3.0	200

